

Mill Test Certificate

Bri-Steel Manufacturing Inc. 2125-64 Avenue, Edmonton, AB Canada T6P 124

Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603 www.bri-steel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-1737 Product Size: 16S100

Production Date: Mar 27, 2014

Production Method: **Hot Expansion**

Product Heat Treatment: As-rolled

ASME B36.10-2004, ASTM/ASME A/SA106-2013 Grade B NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009 MR0103-2010

Certificate No.: MTR- 000985

Product Standards:

Product Markings NPS 16 SCH 100 1.031 INCHWT SMLS 2014/03 NDE

PRODUCT MARKINGS NAME A/SA106 GR B A/SA53 GR B NACE MR0175/MR0103 MADE IN CANADA

PRODUCT MARKINGS NAME A/SA106 GR B A/SA53 GR B NACE MR0175/MR0103 MADE IN CANADA

| | BSM-1737 | | Heat | |
|--|----------------------------|--------------------|--------------|-------------------------|
| | Heat | | Test Type | |
| | NPS 16 SCH 100 1.031in. WT | | Product Size | Product: Details |
| No. of Concession of the Conce | 4 | | Pieces | |
| | DRL | | Length | |
| | 164.8 | lb/ft | Mass | |
| | <5 | µR/hr | Geiger | |
| | <20 | Gauss | Res. Mag. | |
| | Pass | insp. | Visual | |
| | Pass | | OD ** | No |
| | SSEd | TW | TU | n-Destruc |
| | Pass | ASTM E213 | TU | Non-Destructive Testing |
| | SSed | STM E213 ASTM E309 | ET | |
| | • | | HydroTest | |
| | Plain End | Condition | End | |

| | | | | | CI | Chemical Analysis (wt%) | Analysis | (wt%) | | | | | | | | | |
|----------|--|-----------|------|------|-------|-------------------------|----------|-------|------|------|------|-------|-------|-------|--------|---------|---------|
| Heat | Steelmaking Method | Test Type | C | Mn | P | S | iS | Cr | n | Mo | N | ٧ | 1 | Np | 80 | CE(IIW) | CE(CSA) |
| BSM-1737 | Blast Furnace; EAF; Ladle Refining: Vacuum | Heat | 0.21 | 0.90 | 0.017 | 0.002 | 0.29 | 90.0 | 0.06 | 10.0 | 0.02 | 0.004 | 0.002 | 0.001 | 0.0002 | , | , |
| | College a may named | Product | 0.20 | 0.89 | 0.014 | 0.004 | 08.0 | 0.07 | 0.07 | 10.0 | 0.03 | 0.003 | 0.002 | 0.001 | 0.0003 | 0.37 | 0.37 |
| | | | | | | | | | | | | | | | - | | |

| BSM-1737 | | Heat | |
|-----------------------------|------------|------------------|-----------------------|
| 7 Heat | | Test Type | |
| Ferrite & Pearlite | | e Microstructure | |
| 76 HRBW | | Hardness | |
| Pass | | Flattening Test | N |
| Longitudinal; 19.05 mm x WT | 50mm GL | Tension Test | Mechanical Properties |
| 46,500 | psi | Yield (Rt0.5) | |
| 68,000 | psi | Tensile (Rm) | |
| 0.68 | (Rt0.5/Rm) | T/Y | |
| 49 | % | Elongation (A) | |

| Heat | Test | Impact Test | Temp | | Impact | npact Energy | | | % Shea | lear | | | ateral Ex | pansion | |
|----------|----------|----------------|------|---|--------|--------------|-----|---|--------|------|-----|----|-----------|---------|-----|
| | Standard | Sample Details | ů | _ | _ | _ | AVG | % | % | % | AVG | mm | mm | mm | AVG |
| BSM-1737 | 1 | - | • | • | | • | 1 | • | , | • | • | 1 | 1 | ì | , |

Additional Details:

- \checkmark We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in accordance with ASTM/ASME A/SA106-2013 Grade B A/SA53-2012, and the purchase order requirements, and that the results meet the corresponding requirements.
- √ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3. Sour Service-2009 NACE MR0103-2010 Section 2.1
- ✓ No weld repairs have been performed on this product.
- \checkmark This product has not come into contact with mercury during the Bri-Steel Manufacturing processes.
- arphi This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1
- Note that this product was hydrotested to 1000 psi for 5 seconds.
- **OD Tolerances as per API

Mill Test Certificate approved by:

2014 APR 07 Bonden

Assistant QA Manager Paul Sowden, T.T.