

Mill Test Certificate

Bri-Steel Manufacturing Inc

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986 www.bri-steel.com

Seamless Carbon Steel Pipe

Production Method:

Product Markings

Product Heat Number:

BSM-1930 Product Size: 24S60

Production Date:

Jul 09, 2014

Certificate No.: MTR- 001231

Product Standards: ASME B36.10-2004, API 5L-45th Ed. Grade B/X42 PSL1, ASTM/ASME A/SA106-2013 Grade B NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009 MR0103-2010

Hot Expansion **Product Heat Treatment:** As-rolled

	BSM-1930		Heat	
	930			
	Heat		Test Type	
	NPS 24 SCH 60 0.969in. WT		Product Size	Product: Details
	2		Pieces	
	DRL		Length	
	238.1	Ib/ft	Mass	
Section 1	\$	μR/hr	Geiger	
	<10	Gauss	Res. Mag.	
	Ssed	insp.	Visual	
	Pass		OD	No
	Pass	M	TU	Non-Destructive Testing
	Pass	ASTM E213	υT	live Testing
3.00	Pass	ASTM	曰	
	Pass	2970PSI/ 5	HydroTest	
	Plain End	s Condition	End	

| ISPAI-STEEL | SAPI & L/C No.> API SPEC SL NPS 24 SCH 60 0.969 INCHWT GR B/X42 PSL1 SMLS 2014/07 NDE 2970PSI

	BS		
	M-1930	Heat	
Degas, Fully Allied	Blast Furnace; EAF; Ladle Refining; Vacuum	Steelmaking Method	
Product	Heat	Test Type	
0.20	0.20	С	
0.86	0.87	Mn	
0.008	0.011	þ	
0.007	0.009	S	Chemical Analysis (wt%)
0.25	0.24	Si	Analysis (
0.05	0.06	Cr	wt%)
0.09	0.07	C'n	
0.02	0.02	Mo	
0.05	0.06	Ni Ni	
0.003		٧	
0.001		Ti	
0.001		Nb	
0.0003	0.0006	В	
0.37	t	CE(IIW)	
0.37	1	CE(CSA)	
	Product 0.20 0.86 0.008 0.007 0.25 0.05 0.09 0.02 0.05 0.003 0.001 0.001 0.0003 0.37	Heat 0.20 0.87 0.011 0.009 0.24 0.06 0.07 0.02 0.06 0.06 0.0006 - Product 0.20 0.86 0.008 0.007 0.25 0.05 0.09 0.02 0.05 0.003 0.001 0.001 0.0003 0.37	Steelmaking Method Test Type C Mn P S Si Cr Cu Mo Ni V Ti Nb B CE(IIW) Blast Furnace; EAF; Ladle Refining: Vacuum Heat 0.20 0.87 0.011 0.009 0.24 0.06 0.07 0.02 0.06 0.00 0.001 0.001 0.000 0.37 Degas; Fully Killed Product 0.20 0.86 0.008 0.007 0.25 0.05 0.09 0.02 0.05 0.003 0.001 0.001 0.0003 0.37

					Mechanical Properties				
Heat	Test Type	Microstructure	Hardness	Flattening Test	Tension Test	Yield (Rt0.5)	Tensile (Rm)	Τ/Υ	Elongation (A)
					50mm GL	psi	psi	(Rt0.5/Rm)	%
BSM-1930	Heat	Ferrite & Pearlite	77 HRBW	Pass	Longitudinal; 19.05 mm x WT	44,500	65,500	0.68	48
						Committee of the Commit			

Heat	Test	Impact Test	Temp		Impact	Energy			% Shea	lear			Lateral Expans	(pansion	
	Standard	Sample Details	ů	ľ	ſ	ſ	AVG	%	%	%	AVG	mm	mm	mm	AVG
BSM-1930	3				•		,	-	1	-		r	t	-	ı

Additional Details:

✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in accordance with API 5L-45th Ed., ASTM/ASME A/SA106-2013 Grade B A/SA53-2012, and the purchase order requirements, and that the results meet the corresponding requirements.

√ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service-2009 NACE MR0103-2010 Section 2.1

✓ No weld repairs have been performed on this product.

 \checkmark This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

 \checkmark This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

July , 10.2014

Tonya Lam, C.E.T.

Assistant QA Manager