




Mill Test Certificate

Bri-Steel Manufacturing
 2125-64 Avenue, Edmonton, AB Canada T6P 1Z4
 Tel: 001 (780) 469-6603
 Fax: 001 (780) 469-6986
 www.bri-steel.com

Product: Seamless Carbon Steel Pipe Product Heat Number: BSM-3219 Product Size: NPS 20 STD Production Date: Aug 15, 2017
 Production Method: Hot Expansion Product Heat Treatment: Normalizing Forming Certificate No.: MTR- 003477
 Product Standards: ASME B36.10M-2015, API 5L-45th Ed. Grade BN/X42N PSL2, ASTM/ASME A333-2016/SA333-2015 Grade 6 LT(M45C) A106-2014/SA106-2015 Grade B/C NDE, A53-2012/SA53-2015 Grade B Type S, NACE MR0175/ISO 15156-2:2015 MR0103/ISO 17495:2015
 Product Markings:  <API & L/C No.> API SPEC 5L NPS 20 STD 0.375 INCHWT GR BN/X42N PSL2 SMLS 2017/08 NDE 1420PSI
 HEAT BSM-3219 (PIPE # LENGTH MASS) 78.71lb/ft ASTM/ASME A/SA333 GR 6 LT(M45C) A/SA106 GR B/C A/SA53 GR B NACE MR0175/MR0103 MADE IN CANADA

Product: Details						Non-Destructive Testing								
Heat	Test Type	Product Size	Pieces	Length	Mass lb/ft	Geiger μ R/hr	Res. Mag. Gauss	Visual Insp.	OD	UT (WT) ASTM E114	UT ASTM E213	ET ASTM E309	HydroTest 1420PSI/ 5s	End Condition
BSM-3219	Heat	NPS 20 STD 0.375in. WT	13	DRL	78.71	<5	<10	Pass	Pass	Pass	N12.5 Pass	-	Pass	35° Bevel

Chemical Analysis (wt%)																			
Heat	Steelmaking Method	Test Type	C	Mn	P	S	Si	Cr	Cu	Mo	Ni	V	Ti	Nb	B	Mn/C	CE(IIW)	CE(IIW)Max	CE(CSA)
BSM-3219	Blast Furnace; EAF; Ladle Refining; Vacuum Degas; Fully Killed (at TPCO China)	Heat	0.16	1.27	0.010	0.004	0.29	0.05	0.04	0.01	0.02	0.045	0.002	0.001	0.0004	7.94	0.40	-	0.39
		Product	0.17	1.26	0.012	0.007	0.31	0.05	0.04	0.01	0.02	0.045	0.002	0.001	0.0003	7.41	0.40	0.43	0.40
			0.17	1.27	0.011	0.007	0.31	0.05	0.04	0.01	0.02	0.046	0.002	0.001	0.0003	7.47	0.41	0.43	0.41

Mechanical Properties									
Heat	Test Type	Microstructure	Hardness	Flattening Test	Tension Test 2 in. GL	Yield (Rt0.5) psi	Tensile (Rm) psi	Y/T (Rt0.5/Rm)	Elongation (A) %
BSM-3219	Heat	Ferrite & Pearlite	83 HRBW	Pass	Longitudinal; 1.5 in. x WT	52 500	78 500	0.67	37
				Pass	Longitudinal; 1.5 in. x WT	52 500	78 500	0.67	38

Heat	Test Standard	Result	Impact Test Sample Details	Temp °C	Impact Energy Min. (J)	Impact Energy Results (J)	Shear (%)	Lateral Expansion (mm)
					(3 Tests) AVG	(3 Tests) AVG	(3 Tests) AVG	(3 Tests) AVG
BSM-3219	ASTM A333	Pass	CVN Long 8STR 10x7.5mm	-48	(11/11/11) 14	(58/61/98) 72	(20/20/50) 30	(0.97/1.42/2.10) 1.50
BSM-3219	API 5L PSL2	Pass	CVN Trans 8STR 10x7.5mm	0	(15/15/15) 20	(106/93/96) 98	(80/70/70) 73	(2.12/1.77/1.92) 1.94

Additional Details:

✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing in accordance with API 5L-45th Ed., N ASTM/ASME A333-2016/SA333-2015, A106-2014/SA106-2015, A53-2012/SA53-2015, and the purchase order requirements, and that the results meet the corresponding requirements. Bri-Steel Manufacturing is registered and certified to ISO 9001:2015 (APIQR-1584), API Q1, and PED 2014/68/EU.

Mill Test Certificate approved by:

✓ This pipe product meets the **SOUR SERVICE** requirements of ANSI/NACE MR0175/ISO 15156-2A:2015 (Annex A2 for Region 3 Sour Service), and ANSI/NACE MR0103/ISO 17495:2015 Section 13.1

Tilam AUG/22/2017

Tonya Lam, P. Tech (Eng.)
 Assistant QA Manager

- ✓ No weld repairs have been performed on this product.
- ✓ This product has not come into contact with mercury during the Bri-Steel Manufacturing processes.
- ✓ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.